

QUARTZ PLASTER FOR UNDERWATER OR ABOVE WATER FAST SET REPAIRS

E-Z INSTRUCTIONS:

UNDERWATER REPAIRS:

- 1. Remove loose cement and chip area at least 3/8" deep. Make sure the edges are chipped straight down (not beveled or slanted). Clean the surface.
- 2. Add water sparingly to E-Z PATCH® 10 F.S. DRY CEMENT MIX and mix it into a very thick consistency, enough to be used within 5 minutes. Use warm water for even faster set and cold water to slow set.
- 3. Wait a couple of minutes until material starts to harden and then place a little more than needed in your hand or plastic bag. Install E-Z PATCH® 10 F.S. firmly on the area.
- **4.** Slowly flatten smooth with a trowel = flush with the existing plaster and clean the edges with a sponge. Lightly expose the Quartz by troweling or with a sponge. Slowly back away from repair. **Allow repair to set hard before swimming.**

ABOVE WATER REPAIRS:

- 1. Follow steps 1. & 2. above, but add a little more water to the dry mix.
- 2. CRACK REPAIRS: Crack should be saw-cut & cleaned if not a minimum 1/8" wide and 1/4" deep. Rub E-Z PATCH® 10 F.S. deep into crack and remove and expose the Quartz with a moist sponge.
- 3. CHIPS OR LARGER AREAS: Firmly trowel E-Z PATCH® 10 F.S. filling the area. Trowel again (not as firmly) flat and smooth = flush with the existing plaster. Remove excess from edges with a moist sponge. After patch stiffens, trowel again and lightly sponge to reveal Quartz and trowel again to finish. To reveal Quartz, you can also (the next day) wet the area with water and apply 1/3 Muriatic Acid to 2/3 water, lightly scrub with a sponge and then rinse with water within 1 minute. Allow to set hard before filling pool.

To make a Custom Color with any of our cement type repair supplies, use any cement dye.

View our instructional repair video showing how to do this repair at www.e-zpatch.com

E-Z ANSWERS to some Frequently Asked Questions

• Fast Set formulas do not require Liquid Bonder

 Product will cure faster in hotter weather, slower in cooler weather Product is best stored between 30 degrees F and 110 degrees F
WARNING: CONTAINS CEMENT, AN ALKALINE SUBSTANCE IRRITATING TO EYES AND SKIN. SHOULD PRODUCT CONTACT EYES, FLUSH THEM IMMEDIATELY AND REPEATEDLY WITH WATER AND CALL A PHYSICIAN. DO NOT TAKE INTERNALLY. IN CASE OF SKIN CONTACT, RINSE IMMEDIATELY WITH WATER. USE OF RUBBER GLOVES IS RECOMMENDED. KEEP OUT OF THE REACH OF CHILDREN