

YELLOW-TAN COLOR SALTILLO TILE REPAIR

E-Z INSTRUCTIONS:

- **1.** Remove all wax, sealer, debris, tec. from surface to be repaired.
- 2. Add LIQUID CEMENT BONDER to E-Z PATCH 14 DRY CEMENT MIX. .
- **3.** Add water and mix into the consistency of "mashed potatoes". For tile whose color is between Yellow-Tan and Terra Cotta, add **E-Z PATCH 14** and **E-Z PATCH 13** together and mix wet to compare and match the tile surface when it is wet.
- 4. <u>CRACK REPAIR</u>: Rub E-Z PATCH into crack assuring deep penetration into crack (add more water to mix if needed for very small cracks).
- 5. CHIP REPAIR: Fill-in chip and trowel flat.
- **6.** Remove excess immediately with a moist sponge. Rinse Sponge often.
- **7.** Allow repair to dry and then remove any residue with a dry cloth.
- 8. Allow repair to cure two weeks before oiling or sealing.

To make a Custom Color with any of our cement type repair supplies, use any cement dye.

View our instructional repair video showing how to do this repair at www.e-zpatch.com

E-Z ANSWERS to some Frequently Asked Questions

- Liquid Bonder is inside the jar
- · Product will cure faster in hotter weather, slower in cooler weather
- Product is best stored between 40 degrees F and 90 degrees F

<u>WARNING:</u> CONTAINS CEMENT, AN ALKALINE SUBSTANCE IRRITATING TO EYES AND SKIN. CONTAINS ACRYLIC RESIN CEMENT BONDER. SHOULD PRODUCT CONTACT EYES, FLUSH THEM IMMEDIATELY AND REPEATEDLY WITH WATER AND CALL A PHYSICIAN. DO NOT TAKE INTERNALLY. IN CASE OF SKIN CONTACT, RINSE IMMEDIATELY WITH WATER. USE OF RUBBER GLOVES IS RECOMMENDED.

KEEP OUT OF THE REACH OF CHILDREN