



PEBBLE PLASTER REPAIR

E-Z INSTRUCTIONS:

1. Lower water below repair area.
2. Remove loose cement and chip area down at least 3/8" deep. Make sure the edges are chipped straight down (not beveled or slanted). Clean the surface and rinse with water.
3. Add LIQUID CEMENT BONDER to **E-Z PATCH® 9 DRY CEMENT MIX** (use fractions = ¼ of the dry mix to ¼ of the liquid cement bonder, etc.). Now add water and mix until you get the consistency of "mashed potatoes. Use warm water for faster set and cold water to slow set.
- 4a. **CRACK REPAIR** – Saw-cut crack 3/8" wide & 3/8" deep, clean surface Rub **E-Z PATCH® 9** deep into crack and remove excess and expose the Pebble with a moist sponge.
- 4b. **CHIPS OR LARGER AREAS** - Firmly trowel **E-Z PATCH® 9** filling the area. Trowel again flat and smooth = flush with the existing plaster. Remove excess from edges with a moist sponge. Lightly spray with a water hose, bug sprayer or use a wet sponge to expose the Pebble. If there is any residue "haze" the next day, it can be removed by wetting the surface with water & pouring a mixture of 1/3 muriatic acid to 2/3 water on the patched area. Wait 1 minute and rinse using a water hose. **You may refill water the next day.**

To make a Custom Color with any of our cement type repair supplies, use any cement dye.

View our instructional repair video showing how to do this repair at www.e-zpatch.com

E-Z ANSWERS to some Frequently Asked Questions

- Liquid Bonder is inside the jar
- Product will cure faster in hotter weather, slower in cooler weather
- Product is best stored between 40 degrees F and 90 degrees F

WARNING: CONTAINS CEMENT, AN ALKALINE SUBSTANCE IRRITATING TO EYES AND SKIN. CONTAINS ACRYLIC RESIN CEMENT BONDER. SHOULD PRODUCT CONTACT EYES, FLUSH THEM IMMEDIATELY AND REPEATEDLY WITH WATER AND CALL A PHYSICIAN. DO NOT TAKE INTERNALLY. IN CASE OF SKIN CONTACT, RINSE IMMEDIATELY WITH WATER. USE OF RUBBER GLOVES IS RECOMMENDED.

KEEP OUT OF THE REACH OF CHILDREN