


Acrylic Deck Coating



- *Fast Dry Formula*
- *Self-priming, matte finish*
- *Formulated to upgrade concrete pool decks*
- *VOC compliant in the US and Canada*

AVAILABLE IN THESE COLORS



Honey Sand



Whisper White



Sandstone



Dune Shadow



Silver Creek



Cayman Sand

Note: Color differences may occur between actual color chips shown.

Ramuc Acrylic Deck Coating

TECHNICAL INFORMATION

Ramuc® Acrylic Deck Coating is formulated to beautify and upgrade textured concrete deck surfaces while providing a safe, non-slip finish.

This durable product is water-based, featuring soap and water clean-up, and allows a concrete deck or patio to return to service in 48 hours. The coating is colorfast, UV resistant and excellent for restoring bare or previously painted concrete surfaces.

Elevate the aesthetics and functionality of your textured concrete deck surfaces with Ramuc® Acrylic Deck Coating. Designed for both beauty and safety, this coating provides a non-slip finish ideal for high-traffic areas.

VEHICLE TYPE: Acrylic

FINISH: Flat

COLORS: Honey Sand, Whisper White, Sandstone, Dune Shadow, Silver Creek, Cayman Sand

COMPONENTS: 1

WORKING TIME: 30-45 minutes 75°F

SOLIDS BY VOLUME: 42% ± 2%

SOLIDS BY WEIGHT: 61% ± 1%

COVERAGE: 170 ft/gallon @ 4.0 mils

VOC: 190 g/L (as supplied)

FLASH POINT: >200° F (SETA)

STORAGE: Indoors, 60°-100° F

APPLICATION METHOD: Brush, no thicker than 3/8" Mohair or Lambskin roller, Airless or Conventional Spray

RETURN TO SERVICE TIME: 48 hours

NUMBER OF COATS: 2

DRY FILM THICKNESS PER COAT: 2 mils

APPLICATION TEMP: 50°F Min / 90°F Max; surface and ambient

RECOAT TIME: 4 hrs

SHELF LIFE: 3 years from date of manufacture

SURFACE PREPARATION: Coating performance, in general, is proportional to the degree of surface preparation. Follow recommendations carefully, avoiding shortcuts. Inadequate preparation of surfaces will virtually assure inadequate coating performance. Surface must be free of dirt, loose paint, rust, oil, grease, wax, soap and any other foreign matter.



APPLICATION. Stir thoroughly before use. Ramuc® Acrylic Deck Coating may be applied by roller or spray. Apply at the recommended coverage rate. Applying excessively heavy films greater than 60 wet mils will lead to insufficient through-drying and mud cracking of the paint and will yield soft paint films. Do not apply Acrylic Deck Coating on extremely humid days 90°+ RH or when rain is threatening. Do not apply in the late afternoon when working outdoors as the wet film may be adversely affected by dew. When working in cooler temperatures be sure the air and surface temperatures will remain at or above 40°F for at least 8 hours after application.

MIXING THE PAINT: No other primer is recommended or should be used. Mechanically mix the paint to achieve uniform consistency and color. If more than one (1) gallon of paint is used at a time, box (intermix) several gallons together.

CONCRETE: Must be fully cured. If concrete surface has a porous texture, no further surface preparation is necessary. If concrete surface is NOT porous, then acid etching with Ramuc Clean and Prep Solution, sanding or shot blasting is necessary. Make sure to remove all remaining acid with soap and water and scrub brush. (If all acid is not properly removed, you will not create adhesion). Concrete should be completely clean and dry. Patch all imperfections, cracks, etc. with concrete patch filler and flexible joint fillers. **DO NOT USE SILICONE REPAIR PRODUCTS.** After following overcoat instructions, apply two coats of Ramuc Acrylic Deck Coating.

BARE WOOD: Sand surface smooth with 80 grit sandpaper and/or pressure wash well. Fill imperfections; sand flush and clean with Ramuc Clean & Prep Solution. Proceed with the first coat of Ramuc Acrylic Deck Coating. Bare wood that has been epoxied must be thoroughly scrubbed with an ammonia/water solution then sanded with 80 grit sandpaper and solvent cleaned. Proceed with 2 coats of Ramuc Acrylic Deck Coating

BARE FIBERGLASS: The entire surface to be painted regardless of age must be thoroughly prepped to remove all traces of mold release agents and wax. Sand the gel coat with 120 grit sandpaper to a dull, frosty appearance, clean with Ramuc Clean & Prep Solution to remove residue. If the surface is rough or imperfections exist, it will have to be repaired. Fill all nicks and gouges, sand flush when hard, then clean with Ramuc Clean & Prep Solution. Proceed with 2 coats of Ramuc Acrylic Deck Coating.

PAINTED SURFACES: Clean painted areas with Ramuc Clean & Prep Solution. If the old paint is an oil-based enamel or polyurethane, and is in good, sound condition, sand it thoroughly smooth with 80 - 100 grit sandpaper, solvent clean to remove residue with Ramuc Clean & Prep Solution. If the old oil-base or polyurethane paint contained a non-skid material, scrub the non-skid surface well with cleaner. Thoroughly rinse the surface and allow to dry, then apply two coats of Ramuc Acrylic Deck Coating. If the old paint is in poor condition, remove it with chemical stripper or by sanding. Proceed with instructions for the appropriate bare surface system.

CLEAN UP: Soap and water.
