

EPOXY-BASED			ACRYLIC-BASED	
HI BUILD EPOXY	EP EPOXY	SLIDE COAT	DS	
<ul style="list-style-type: none"> <li>• New/Bare/Sandblasted concrete</li> <li>• Plaster</li> <li>• Gunite</li> <li>• Marcite</li> <li>• Sandblasted steel</li> <li>• Bare fiberglass</li> <li>• Existing epoxy coated surfaces</li> </ul>	<ul style="list-style-type: none"> <li>• New/Bare/Sandblasted concrete</li> <li>• Plaster</li> <li>• Marcite</li> <li>• Bare fiberglass</li> <li>• Existing epoxy coated surfaces</li> </ul>	<ul style="list-style-type: none"> <li>• New/Bare/Sandblasted concrete</li> <li>• Plaster</li> <li>• Marcite</li> <li>• Bare fiberglass</li> <li>• Existing epoxy coated surfaces</li> </ul>	<ul style="list-style-type: none"> <li>• Existing acrylic</li> <li>• Existing chlorinated and synthetic rubber</li> <li>• Bare concrete</li> </ul>	<b>SURFACE TYPES</b>
Ramuc Clean & Prep Solution	Ramuc Clean & Prep Solution	Ramuc Clean & Prep Solution	Ramuc Clean & Prep Solution	<b>PREP AGENT</b>
<ul style="list-style-type: none"> <li>• Chlorinated rubber</li> <li>• Synthetic rubber</li> <li>• Acrylic</li> </ul>	<ul style="list-style-type: none"> <li>• Chlorinated rubber</li> <li>• Synthetic rubber</li> <li>• Acrylic</li> </ul>	<ul style="list-style-type: none"> <li>• Chlorinated rubber</li> <li>• Synthetic rubber</li> <li>• Acrylic</li> </ul>	<ul style="list-style-type: none"> <li>• Fiberglass</li> <li>• Gelcoat</li> <li>• Spas/Hot tubs</li> <li>• Metal</li> <li>• Salt water pool systems</li> <li>• Existing epoxy</li> </ul>	<b>DO NOT APPLY TO (NON-COMPATIBLE SURFACES OR COATINGS)</b>
Satin	High-gloss	High-gloss	Matte	<b>FINISH</b>
1 & 2 gallon kits	1 gallon kit	Half gallon kit (2 quarts)	1 & 5 gallon	<b>PACKAGE SIZE</b>
<ul style="list-style-type: none"> <li>• 75-100 sq. ft./gallon kit on bare or rough, porous surfaces</li> <li>• 150-175 sq. ft./gallon kit on recoats</li> </ul>	<ul style="list-style-type: none"> <li>• 175-200 sq. ft./gallon kit on bare sandblasted or rough surfaces</li> <li>• 400-450 sq. ft./gallon kit on recoats</li> </ul>	150 sq. ft./half gallon kit on bare sandblasted or rough surfaces	<ul style="list-style-type: none"> <li>• 250 sq. ft./gallon on bare surfaces</li> <li>• 350-400 sq. ft./gallon on recoats</li> </ul>	<b>COVERAGE</b>
6-8 years	3-5 years	4 years	1-2 years	<b>SERVICE LIFE</b>
<ul style="list-style-type: none"> <li>• Brush</li> <li>• Roller (max 3/8" thickness)</li> <li>• Airless or conventional sprayer</li> </ul>	<ul style="list-style-type: none"> <li>• Brush</li> <li>• Roller (max 3/8" thickness)</li> <li>• Airless or conventional sprayer</li> </ul>	<ul style="list-style-type: none"> <li>• Brush</li> <li>• Roller (max 3/8" thickness)</li> <li>• Airless or conventional sprayer</li> </ul>	<ul style="list-style-type: none"> <li>• Brush</li> <li>• Roller (max 3/8" thickness)</li> <li>• Airless or conventional sprayer</li> </ul>	<b>APPLICATION</b>
16-72 hours (After 72 hours, must sand before applying second coat)	12-72 hours (After 72 hours, must sand before applying second coat)	2 hours	4 hours	<b>DRY TIME BETWEEN COATS</b>
<ul style="list-style-type: none"> <li>• Outdoor: 5-7 days</li> <li>• Indoor: 10-14 days</li> </ul>	<ul style="list-style-type: none"> <li>• Outdoor: 5-7 days</li> <li>• Indoor: 10-14 days</li> </ul>	24 hours	<ul style="list-style-type: none"> <li>• Outdoor: 3 dry days</li> <li>• Indoor: 6 days</li> </ul>	<b>DRY/CURE TIME BEFORE FILLING</b>
Ramuc Thinner	Ramuc Thinner	Ramuc Thinner	Soap and water	<b>CLEAN-UP</b>
Yes	Yes	Yes	Yes	<b>VOC COMPLIANT</b>